

**651503005**
**COATED -PE300- YG\_D**

<b>Face</b>	One side coated paper is designed for high-end, pressure sensitive label applications. This grade features excellent opacity and high brightness combined with a semi-gloss finish for excellent printability.
<b>Adhesive</b>	Acrylic based, strong permanent adhesive for general use. This adhesive gives excellent initial tack and adhesion even on a wide variety substrates including apolar, rough and curved substrates. Edge bleeding may occur.
<b>Liner</b>	Yellow, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

<b>Face</b>	<b>Method</b>	<b>Unit</b>	<b>Target</b>	
Basis Weight	ISO 536	g/m <sup>2</sup>	78 ± 4	
Thickness	ISO 534	µm	67 ± 4	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min.275	(min. 6,875 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.550	(min. 13,75 N/25mm)
Min. appl temperature		°C	+5	
Service temperature		°C	-20 / +80	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	56 ± 2	
Thickness	ISO 534	µm	50 ± 3	
Transparency	DIN 53147	%	49	
<b>Laminate</b>				
Thickness	ISO 534	µm	130 ± 5	

**Application and use**

This product is designed for wide range of promotional and industrial labelling applications where a good semi gloss appearance is required.

**Packaging**

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

**Conversion and Printing**

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

**Shelf Life and Storage Conditions**

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.